

## Cast Inoculants

	SI (%)	Ba (%)	Sr (%)	Zr (%)	TRE (%)	Al (%)	Ca (%)	Mn (%)	Bi (%)
75 - INOCULANT	70 - 75					0.6 - 1.5	0.6 - 1.5		
SNAM HIAL™	70 - 75					3.5 - 4.5	0.5 - 1.5		
SNAM ZIMAN™	60 - 69	0.3 - 1.0		2.0 - 3.0		0.5 - 1.5	0.5 - 2.0	1.9 - 2.8	
SNAM HIMAN™	60 - 65	4.0 - 6.0				1.0 - 1.5	1.0 - 1.5	9.0 - 11.0	
SNAM STRON™ 75	70 - 75		0.6 - 1.0			0.5 Max	0.1 Max		
SNAM STRON™ 50	46 - 50		0.6 - 1.0			0.5 Max	0.1 Max		
SNAM RECAL™	70 - 75				1.5 - 2.0	0.5 - 1.0	0.5 - 1.0		
SNAM BACAL™	70 - 75	0.75 - 1.25				0.75 - 1.25	0.75 - 1.25		
SNAM BACAL™ 50	50 - 60	0.75 - 1.25				0.75 - 1.25	0.75 - 1.25		
SNAM HI BACAL™	65 - 75	2.0 - 3.0				0.5 - 1.5	1.0 - 2.0		
SNAM ZIRCAL™	70 - 75			1.0 - 2.0		1.0 - 1.5	1.5 - 2.5		
SNAM BIAL™	60 - 70				0.6 - 1.0	0.8 - 1.5	1.0 - 1.5		0.8 - 1.0
SNAM LACAL™	50 - 60				La : 1.75 - 2.25	0.8 - 1.25	1.8 - 2.5		
SNAM XBACAL™	60 - 65	7.0 - 11.0				0.8 - 1.5	0.8 - 1.5		

Standard Sizes : 0.5 - 2mm, 0.5 - 3mm, 0.2 - 0.5mm, 0.2 - 0.7mm, 2 - 6mm, 2 - 10mm & 6 - 12mm.  
Can also supply according to customer's requirement.

Standard Packing : 25 kgs Bags, 50 kgs Bags, 100 kgs Bags, 250 kgs Bags, 500 kgs Bags, 1000 kgs Bags, 100 kgs Drums & 250 kgs Drums.  
Can also supply according to customer's requirement.