

FERRO SILICON

GRADE	Si	C	S	P	Al	Ca	SIZE
		Max.	Max.	Max.	Max.	Max.	Min.
FeSi73A105	70 - 75	0.15	0.050	0.050	0.50	1.00	+/-10% 25 - 150
FeSi65	60 - 70	0.15	0.050	0.050	1.00	1.00	25 - 150

In Percent

Note : Specification as per IS 1110 : 1990 (Fourth Revision)

Snam Alloys has made its mark in the area of Ferro Silicon and has controlled Aluminium and Calcium content to find application in the making of cast iron, spring steel and other high silicon steels. The product's special feature is the ability to raise the bath temperature when added to molten steel in the ladle.

Snam Alloys also offers low aluminium grades of Ferro Silicon as deoxidising agents in continuous casting of steel and standard Ferro Silicon grades.

Snam Alloys Pvt. Ltd.

Kariamianickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : info@snam.co.in website: <http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

