

FERRO SILICON MAGNESIUM FOR CGI (SNAM CGMG)

ELEMENT	PERCENTAGE
SILICON	43 - 48%
CALCIUM	1.75 - 2.25%
ALUMINIUM	1.0 % MAX.
RARE EARTHS	5.50 - 6.50%
MAGNESIUM	5.0 - 6.0%
IRON	REST

Sizing : 5-25mm, 2-20mm, Can also supply according to customer's requirement.

Standard Packing : 25 Kgs. Bags, 50 Kgs Bags, 100 Kgs Drums, 100 Kgs Bags, 250 Kgs Drums, 1000 Kgs Bags. Can also supply according to customer's requirement.

SUGGESTED APPLICATION:

- SNAM CGMG** is used for manufacture of Compacted Graphite Iron (CGI)
- SNAM CGMG** is best suited for all section thickness
- Use of **SNAM CGMG** gives Titanium free alternative for manufacture of CGI
- Lower treatment cost
- Can maintain High Silicon levels in base metal
- Low dross / slag formation
- Better machinability of castings

NOTE

Snam can provide technical know how for manufacture of CGI. Please contact Snam or its agents for more information.

Snam Alloys Pvt. Ltd.

Kariamianickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : info@snam.co.in website: <http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

