

SNAM FESICAL[®]

ELEMENT	PERCENTAGE
SILICON	70 - 75%
CALCIUM	0.60 - 1.50%
ALUMINIUM	0.60 - 1.50%

Standard sizes : 6 - 12 mm, 2 - 10 mm, 2 - 6 mm, 2 - 4 mm, 0.5 - 3 mm, 0.5 - 2 mm, 0.2 - 0.5 mm, 0.2 - 0.7 mm & 0 - 0.2 mm. Can also supply according to customer's requirement.

Standard Packing : 25 Kgs. Bags, 50 Kgs Bags, 100 Kgs Drums, 100 Kgs Bags, 250 Kgs Drums, 1000 Kgs Bags. Can also supply according to customer's requirement.

These inoculants are made by chemical mixing by adding calcium and aluminium into molten Ferro Silicon. Because of controlled chemistry the effect of inoculation of flake graphite irons are:

- to reduce chill and promote graphite
- to reduce fine graphite and associated ferrite
- to promote uniform structures
- to obtain a small increase in strength

In ductile irons the principal effects are:

- to reduce chill,
- to provide general improvement in properties and
- to encourage formation of well shaped nodules.

Snam Alloys Pvt. Ltd.

Kariamianickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : info@snam.co.in website: <http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

