

SNAM LACAL[®]

ELEMENT	PERCENTAGE
SILICON	50 - 60%
CALCIUM	1.80 - 2.50%
ALUMINIUM	0.80 - 1.25%
LANTHANUM	1.75 - 2.25%
IRON	REST

Standard sizes : 6 - 12 mm, 2 - 10 mm, 2 - 6 mm, 2 - 4 mm, 0.5 - 3 mm, 0.5 - 2 mm, 0.2 - 0.5 mm, 0.2 - 0.7 mm & 0 - 0.2 mm. Can also supply according to customer's requirement.

Standard Packing : 25 Kgs. Bags. 50 Kgs Bags, 100 Kgs Drums, 100 Kgs Bags, 250 Kgs Drums, 1000 Kgs Bags. Can also supply according to customer's requirement.

SUGGESTED APPLICATION:

- SNAM LACAL[®]** is best suited for inoculation of Ductile and Vermicular iron.
- SNAM LACAL[®]** is very effective for chill reduction
- SNAM LACAL[®]** is very effective for shrinkage control
- SNAM LACAL[®]** helps in minimizing micro porosities
- SNAM LACAL[®]** helps in controlling the effect of undesirable elements in iron

NOTE

Addition at metal stream into the pouring ladle gives good dissolution and best results.

Snam Alloys Pvt. Ltd.

Kariamianickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : info@snam.co.in website:<http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

