

## FERRO SILICON MAGNESIUM (SNAM LAMG®)

ELEMENT	LAMG - 1	LAMG - 3
SILICON	43 - 48%	43 - 48%
CALCIUM	0.80 - 1.20%	2.8 - 3.3%
ALUMINIUM	1.0 % MAX.	0.4 - 1.0%
LANTHANUM	0.50 - 0.75 %	0.35 - 0.55%
MAGNESIUM	5.0 - 6.0%	5.55 - 6.15%
IRON	REST	REST

**Sizing :** 4-32mm, 5-20mm, 5-25mm, 2-20mm, Can also supply according to customer's requirement.

**Standard Packing :** 25 Kgs. Bags, 50 Kgs Bags, 100 Kgs Drums, 100 Kgs Bags, 250 Kgs Drums, 1000 Kgs Bags. Can also supply according to customer's requirement.

### SUGGESTED APPLICATION:

- SNAM LAMG® is used for manufacture of ductile iron
- SNAM LAMG® gives improved nodule count and nodularity
- SNAM LAMG® helps in reduction of shrinkage porosity
- SNAM LAMG® helps in reducing formation of carbides
- SNAM LAMG® gives more uniform Nodule size distribution

## Snam Alloys Pvt. Ltd.

Kariamanickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199  
e.mail : info@snam.co.in website: <http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

