

SNAM RECAL[®]

ELEMENT	PERCENTAGE
SILICON	70 - 75%
CALCIUM	0.50 - 1.0%
CERIUM	1.50 - 2.0%
ALUMINIUM	0.50 - 1.0%
IRON	BALANCE

Standard sizes : 6 - 12 mm, 2 - 10 mm, 2 - 6 mm, 2 - 4 mm, 0.5 - 3 mm, 0.5 - 2 mm, 0.2 - 0.5 mm, 0.2 - 0.7 mm & 0 - 0.2 mm. Can also supply according to customer's requirement.

Standard Packing : 25 Kgs. Bags. 50 Kgs Bags, 100 Kgs Drums, 100 Kgs Bags, 250 Kgs Drums, 1000 Kgs Bags. Can also supply according to customer's requirement.

Suggested Application:

- **SNAM RECAL[®]** is very effective in Ductile Iron / S G Iron by retarding chill formation even in thin sections.
- **SNAM RECAL[®]** ensures good nodularity with good nodule count.
- **SNAM RECAL[®]** neutralises subversive trace elements which retards Nodularisation.

Rate of Addition : 0.3 to 0.6% as post treatment inoculation for Ductile / SG Iron.

Note : Addition at metal stream into the pouring ladle gives good dissolution and best results.

Snam Alloys Pvt. Ltd.

Kariamianickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : info@snam.co.in website:<http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

