

SNAM STRON[®] 50

ELEMENT	PERCENTAGE
SILICON	50 - 60%
CALCIUM	0.10% max
STRONTIUM	0.60 - 1.00%
ALUMINIUM	0.50% max.
IRON	BALANCE

Standard sizes : 6 - 12 mm, 2 - 10 mm, 2 - 6 mm, 2 - 4 mm, 0.5 - 3 mm, 0.5 - 2 mm, 0.2 - 0.5 mm, 0.2 - 0.7 mm & 0 - 0.2 mm. Can also supply according to customer's requirement.

Standard Packing : 25 Kgs Bags, 50 Kgs Bags, 100 Kgs Drums, 100 Kgs Bags, 250 Kgs Drums, 1000 Kgs Bags. Can also supply according to customer's requirement.

Suggested Application:

- **SNAM STRON[®] 50** is best suited for Flake Graphite Iron, Particularly where very low Al & Ca is desired.
- **SNAM STRON[®] 50** ensures type 'A' graphite and reduces Ferrite associated with graphite.
- **SNAM STRON[®] 50** gives low dross formation due to control on Ca.
- Less tendency for Pin Hole defects due to control on Al.
- Extended pouring time as **SNAM STRON[®] 50** delays the inoculation fading.
- **SNAM STRON[®] 50** can be used for Ductile / SG Iron as late inoculation particularly where Ca & Ce levels are low.

Rate of Addition : 0.2 to 0.5% as post treatment inoculation for Ductile / SG Iron.
0.1 to 0.3% in metal stream for Flake graphite Iron.

Note : Addition at metal stream into the pouring ladle gives good dissolution and best results.

Snam Alloys Pvt. Ltd.

Kariamianickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : info@snam.co.in website: <http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

