

SNAM X BACAL[®]

ELEMENT	PERCENTAGE
SILICON	60 - 65%
CALCIUM	0.80 - 1.50 %
ALUMINIUM	0.80 - 1.50%
BARIUM	7.0 - 11.0%
IRON	REST

Standard sizes : 6 - 12 mm, 2 - 10 mm, 2 - 6 mm, 2 - 4 mm, 0.5 - 3 mm, 0.5 - 2 mm, 0.2 - 0.5 mm, 0.2 - 0.7 mm & 0 - 0.2 mm. Can also supply according to customer's requirement.

Standard Packing : 25 Kgs. Bags. 50 Kgs Bags, 100 Kgs Drums, 100 Kgs Bags, 250 Kgs Drums, 1000 Kgs Bags. Can also supply according to customer's requirement.

SUGGESTED APPLICATION:

- SNAM X BACAL[®]** is best suited for inoculation of Ductile iron.
- SNAM X BACAL[®]** is very effective as a ladle inoculant
- SNAM X BACAL[®]** has a long fade time.
- SNAM X BACAL[®]** helps in improving nodularity and nodule count.
- SNAM X BACAL[®]** helps in reduction of carbide formation.
- SNAM X BACAL[®]** is a very good pre conditioner and can be added in the furnace.

Snam Alloys Pvt. Ltd.

Kariamanickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : info@snam.co.in website:<http://www.snam.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

